

GENERAL DESCRIPTION:

WELD-ON[®] 810[™] is a white, low VOC emission, thick syrupy, two-component, high strength reactive adhesive. It has a fast cure time, withstands very high pressure and is high impact resistant.

APPLICATION:

WELD-ON 810 is specially formulated for bonding large diameter PVC and CPVC pipe and fittings. It also bonds ABS, Styrene, Acrylic, FRP (fiberglass-reinforced polyester), concrete, clay and other materials to themselves or to dissimilar materials. It is great for repairing cracks or leaky pipe valves and fittings. WELD-ON 810 has excellent gap-filling property and is ideal for fabricating fittings and joining saddles to pipe. It also provides excellent adhesion in peel, tensile or sheer applications. For joints subjected to chemical exposure, prior evaluation must be made of the specific chemical concentration, temperature and pressure involved and the compatibility with WELD-ON 810. Not recommended for use on Neoprene, Delrin, PTFE, Silicone, Polypropylene, Polyethylene and other Polyolefins or joints with an interference fit.

AVAILABILITY:

This product is available in 4-ounce (118 ml), pint (473 ml), quart (946 ml) and gallon (3.785 l) two-part, pre-measured, plastic container kits. See our current Price List for detailed information on containers and applicators. For convenient dispensing format, refer to WELD-ON® 811[™] which is packaged in 470 ml dual cylinder cartridge and dispensed via dispensing gun and mixing tip.

STANDARDS AND CERTIFICATION LISTINGS:

- Meets SCAQMD Rule 1168
- Compliant with LEED[®] (Leadership in Energy and Environmental Design). When using this Weld-On low VOC product, credit can be claimed for LEED Green Building Rating System Indoor Environmental Quality.

SPECIFICATIONS:

COLOR:	White
RESIN:	Acrylic
SPECIFIC GRAVITY:	1.03 ± 0.04
BROOKFIELD VISCOSITY:	Minimum 30,000 cps @ 73° ± 3.6°F
APPROXIMATE COVERAGE:	14 sq. ft. per pint*
	115 sq. ft. per gallon*
	*Based on laboratory evaluation @ 20 mil thickness. This data is for reference only.
	Actual coverage may vary.

DIRECTIONS FOR USE: SUBSTRATES PREPARATION

Bonding surfaces must be clean and dry. If the surfaces are hard and glossy, abrading (sanding) and priming with a degreasing solvent is recommended. Chlorinated solvents, methyl ethyl ketone, acetone and/or rubbing isopropyl alcohol may be used to remove grease and/or dirt.

INSTALLATION

1. Assemble materials for the job: WELD-ON 810 kit, clean mixing sticks, applicators (spatula or stiff brush), sandpaper, clean wiping cloth, cleaning solvent and gloves.

2. Prepare joints by sanding to roughen mating surfaces. Wipe surfaces clean with a dry rag or solvent cleaner. Do not soften surfaces with solvent cleaner.

3. WELD-ON 810 kit has a mixing ratio of 100:13 and both components are packaged and pre-measured to this ratio. Add Catalyst B (small container) to Resin A (large container). Mix thoroughly and apply to each mating surface. Pot life and working time is about 30 minutes at 70°F (21°C).

4. Assemble parts and allow squeeze out to remain as filler.

5. Allow the joined surfaces to cure undisturbed. Recommended set time is 1 hour. Recommended cure time is 2 hours to reach 80% bond strength (resin layer cures to a hard gel), 24 hours to reach near ultimate strength. The cured layer is a tough, chemical and water resistant plastic.

Note: Warmer weather will shorten pot life and cure time. Colder weather will increase the time for both. Applying heat may speed up the cure time. When joining CPVC for service temperatures over 150°F (65°C), please contact WELD-ON for more information.





REPAIR

Replacing a failed joint with new material and taking greater care in the joining process is always preferred. This repair is for leaks only and ideal for area where the joint cannot be cut out. Do not use this method if the pipe has separated from the fitting.

- 1. Assemble materials for the job: WELD-ON 810 kit, clean mixing sticks, applicators (spatula or stiff brush), fiberglass cloth mat cut to desirable size for wrapping the leaked pipe, sandpaper or emery, clean wiping cloth, and gloves.
- 2. Turn off water pressure. Dry off the bonding area and abrade it well with sandpaper and wipe clean.
- 3. Prepare WELD-ON 810 adhesive. Add Catalyst B (small container) to Resin A (large container) and mix thoroughly.
- 4. Apply a generous coat of adhesive mixture to leakage and surrounding area.
- 5. Apply the adhesive mixture to the mating surface of fiberglass cloth. Wrap cloth around the leaked pipe. Some adhesive should squeeze up through cloth. Note: Fiberglass cloth is recommended for added structural strength to the leaked pipe. Good bonding result is also achievable without using the cloth.
- 6. Apply an additional coat of WELD-ON 810 adhesive to the top surface.
- 7. Allow to cure for a minimum of 4 hours at 70°F (21°C). Overnight or 24 hours cure is desirable before re-pressurizing the systems.

SHELF LIFE:

1 year in unopened containers when stored between 50°F (10°C) and 80°F (27°C). Keep away from sources of heat, sunlight and moisture.

QUALITY ASSURANCE:

WELD-ON 810 is carefully evaluated to assure that consistent high quality is maintained. Fourier transform infrared spectroscopy, gas chromatography, and additional in depth testing ensures each batch is manufactured to exacting standards. A batch identification code is stamped on each can and assures traceability of all materials and processes used in manufacturing this product.

IMPORTANT NOTE:

This product is intended for use by skilled individuals at their own risk. These suggestions and data are based on information we believe to be reliable. Installers should verify for themselves that they can make satisfactory joints under varying conditions. Toward this end, it is highly desirable that they receive personal instruction from trained instructors or competent, experienced installers. Contact Weld-On or your supplier for additional information or instructions.

Refer to the current WELD-ON 810[™] GHS Safety Data Sheet for additional safety precautions, first-aid, handling, storage and transportation information.

WARRANTY:

Weld-On Adhesives, Inc., warrants to all original purchasers of Weld-On products that all new Weld-On products shall be of good quality and free from defects in material and workmanship for the product's shelf life. If any Weld-On product becomes defective, or fails to conform to this written limited warranty under normal use and storage conditions, and if the original purchaser complies with the terms of this limited warranty, then Weld-On will, without charge, replace the nonconforming product.

This limited warranty shall extend to all products manufactured and sold by Weld-On. However, this limited warranty shall not extend to, nor shall Weld-On be responsible for, damages or loss resulting from accident, misuse, negligent use, improper application, or incorporation of Weld-On products into other products. In addition, any repackaging of Weld-On products also shall void the limited warranty provided herein.

Any defective Weld-On products shall be replaced pursuant to the terms of this limited warranty by returning the defective product, with transportation charges prepaid, to Weld-On at the following address: Weld-On Adhesives, Inc. Attn: Customer Service 455 West Victoria Street Compton, CA 90220

Any implied warranty in connection with any Weld-On product hereby is limited in duration to the period of this limited warranty. Weld-On shall not be responsible for, nor does this limited warranty extend to, consequential damage, or incidental damage or expense, including without limitation, injury to persons or property or loss of use. This limited warranty is in lieu of all other express warranties of Weld-On, and Weld-On does not assume, nor does it authorize any person to assume on its behalf, any other obligation or liability.

